

# Review on A Golden Fiber: Jute and its By Products

## **ABSTRACT:**

The use of agricultural waste for any type of uses is limited in developing countries. For this study we have selected Jute i.e. Golden Fibre. The traditional uses of this have been sustained in packing, carpet backing, biomass energy after few operations, handmade paper etc. The aims of this study were therefore (i) To summarize the production data in India State wise and year wise. (ii) Special and specific properties of whole jute. (iii) Uses of jute as per its part: **Jute sticks, Jute Caddies, Jute Leaves, Jute Root Cuttings** in different areas. And after summarize all the uses; it is clear that these parts are not used efficiently. There is some gap between farmers and industrial uses. If these parts can be utilized effectively in the development of value added products, it will certainly strengthen the economy of poor farmers and country also.

Key Words: Jute Sticks, Jute Caddies, Paper, Biomass, Composite.

## **INTRODUCTION**

In India, the industrialization of paper is approximately 110 years old, and is continuously increasing year by year. This industry is directly dependent upon the raw materials of cellulose which is obtained from the forest resources (resources such as hardwood/bamboo etc), agricultural residue (straw and bagasse etc) and waste paper as well. Forest resources are unable to supply the raw materials needed to produce medium- and high-quality paper at the required growth rate, and the pulp made from agricultural residues is of lower quality. In order to meet the demand for high-quality products, it is necessary to search for an alternative to fibrous raw materials. Recently, whole jute or kenaf has gained popularity as a potential source of fibre due to its strengthening qualities, which are comparable to those of hardwood. (<http://www.dcpulppaper.org/gifs/report41.pdf>)

Jute fiber plays an important role in Median economy. It is obtained from two cultivated species viz. *C. capsularis* & *C. olitorius* [1]. These are known as 'white' and 'tossa' jute respectively. In India, these are cultivated in the states of West Bengal, Bihar, Uttar Pradesh, Assam, Meghalaya, Orissa, and Tripura. The other jute producing countries are Bangladesh, China, Nepal, Myanmar(Burma), Thailand and Indonesia.

The plant parts after extraction of fiber viz. leaves, root cuttings, sticks and mill waste, caddies are not used efficiently. Therefore, the farmers get a very low return to this cash crop. However, if these parts can be utilized effectively in the development of value added products it will rather strengthen the economy of poor farmers [2].

The Jute industry generates about 40,000 tonnes of processing waste as by products, commonly known as *Jute Caddies* [3]. The major constituent of this waste is unspinnable jute fiber. The other constituents are batching oil, machine oil, barks and inorganic dirt. These waste materials can be used for a variety of purposes, such as the creation of biogas, non-woven goods, biomass energy, and handmade paper. They can also help to further sustainable development.[4].

### **STRUCTURE:**

The Jute plant is an annual plant and grows to a height of 5- 16 feet and normally do not have significant branches. The diameter of the stem may reach up to 10 to 20 mm on maturity. The stem portion has two distinct zones viz. bark and core. The bark portion becomes loosely attached to core when the plant is dry. The dry bark is dark brown in color and the core (wood) is pale yellow or cream colored.

### **PHYSICAL AND CHEMICAL PROPERTIES:**

The physical properties of Jute raw material are furnished in Table 1. 36% of the total weight of the jute is made up of bast fibre, with core wood making up the remaining 64%. It should be observed that the bulk densities of entire jute and jute bast fibre are significantly lower than those of hardwood and softwood, respectively, and core wood. There are drawbacks to the raw jute fiber's bulkiness in terms of volumetric loading, etc. Impregnation of chips with liquor also is affected due to high bulkiness, as the chips tend to float.

**Table 1: Physical Properties**

S.N.	Particulars	Whole Jute	Bast Fibre	Core Fibre
1	Ratio of Bast and Core, %	-	36	64
2	Bulk Density, kg/m <sup>3</sup>	93.4	69.2	110.5

A complete proximate analysis of whole jute, bast fiber and core wood was carried out. The results are furnished in Table 2. Because the bast component contains superfluous silica, the ash concentration of the bast is higher. In comparison, the amount of holo-cellulose in the bark is greater. Thus, a higher  $\alpha$ -cellulose concentration in the bark predicts a much higher pulp yield level and an increase in pulp strength at the same time. ([http://jute.org/project\\_reports/Final%20Report%20-%20CPPRI.pdf](http://jute.org/project_reports/Final%20Report%20-%20CPPRI.pdf))

**Table 2: Chemical Properties of Raw Materials**

S.N.	Particulars	Whole Jute	Bast Fibre	Core Fibre
------	-------------	------------	------------	------------

1	Ash Content, %	3.58	4.43	1.89
2	Cold Water Solubility, %	4.12	4.51	2.44
3	Hot Water Solubility, %	4.88	8.57	2.98
4	1/10 NaOH Solubility, %	26.21	30.05	23.30
5	Alcohol Benzene, %	2.65	3.73	2.75
6	Klasson Lignin, %	21.13	15.30	24.23
7	Acid Soluble Lignin, %	1.04	1.10	1.20
8	Holo-cellulose, %	79.50	81.40	75.50
9	$\alpha$ - Cellulose, %	43.52	54.72	36.50
10	$\beta$ - Cellulose, %	19.88	14.60	25.90
11	$\lambda$ – Cellulose, %	16.15	12.08	13.10
12	Pentosan, %	15.3	14.57	16.04

A lot of short fibers with dust gets accumulated on the mill floors as droppings, and are called Caddies. The basic chemical composition of caddies are more or less similar to that of jute fibers except that it contains residual of mineral oil applied at the time of Piling. In jute sector of Industries the major industrial waste product is Caddy. The proximate analysis of the jute caddies shows a volatile matter at 40 percent, fixed carbon 12-13 percent with gross calorific value as 3200-3300 kcal/kg[5]. Jute caddies constitute about 4-6 percent of total jute consumed in the mills. The jute caddies are cleaned and scoured. The key component in this process is the binder, which can be applied in either a liquid or solid state depending on the binder and the finished product. The most significant binders include acrylic resin, rubber latex, polyvinyl acetate, polyvinyl chloride, dextrin, carboxymethyl cellulose, and phenol formaldehyde. They can be used separately or in combination. The steps in the procedure are as follows, to put it briefly:

1. Preparatory step (opening and blending)
2. Web formation
3. Impregnation with the binder
4. Drying and curing
5. Finishing.

#### **Production Statistics:**

The state wise jute production during last few years is shown in the given Table 3. It shows that West Bengal and Bihar are the leading jute growing states in India.

(<http://jutecomm.gov.in/statewise%20P%20&%20R%20jute.htm>Jute commissioner, Govt. of India, Ministry of textile)

**Table 3: State wise Production:**

STATE WISE PRODUCTION & RAW JUTE				QTY : IN lakh bales		
(A = Area IN '000 Hect.; P = Prod. In '000 bales of 180 k.g per bale ; PY = Productivity in QTLS/Hect.)						
(APRIL / MARCH)	2012 – 2013			2013 - 2014		
	A	P	PY	A	P	PY
STATE						
ASSAM	70	823	2166	81	823	1829
MEGHALAYA	12.6	86.31	1236	0	0	0
WEST BENGAL	577	8349	2605	0	0	0
BIHAR	139.1	1690	2182	0	0	0
ORISSA	22.4	177.7	1427	578	8522	2654
ANDHRA PRADESH	25	225	1620	133	1540	2084
TRIPURA	1.3	11	1523	22	176	1440
NAGALAND	4.63	40.2	1564	15	142	1704
UTTAR PRADESH	0.4	4.5	2025	1.2	9.8	1470
OTHERS	20	0	0	36.3	203.6	1010
TOTALS	827.7	11406.7	2353	866.5	11416	2372

STATE WISE PRODUCTION & RAW JUTE				QTY : IN lakh bales		
(A = Area IN '000 Hect.; P = Prod. In '000 bales of 180 k.g per bale ; PY = Productivity in QTLS/Hect.)						
(APRIL / MARCH)	2014-2015			2015-2016		
	A	P	PY	A	P	PY
STATE						
ANDHRA PRADESH	7	50	1286	5.6	0	0
ASSAM	75	795	1908	76.4	767	1917
BIHAR	111.2	1500	2428	113.4	0	0
CHATTISGARH	1.1	2.2	360	0	0	0
JARKHAND	0	0	0	0	0	0
KARNATAKA	0	0	0	0	0	0
MADHYA PRADESH	0.3	0.8	480	0	0	0
MAHARASTRA	0	0	0	0	0	0
MEGHALAYA	0	0	0	8	0	0
NAGALAND	0	0	0	3	0	0
ORISSA	12.9	67.8	946	14.3	0	0
TAMIL NADU	0.2	4.3	3870	0	0	0
TRIPURA	0	0	0	1.1	0	0

UTTAR PRADESH	0	0	0	0	0	0
WEST BENGAL	576.1	8969	2802	519	8075	2801
OTHERS	19.1	104.9	989	1.7	0	0
TOTALS	802.9	11494	2577	742.5	8842	

The total area under Jute Cultivation is about 0.80 million hectares and the production is approximately 10 million bales i.e. 1.8 million tones.

### **CONVENTIONAL USES OF JUTE:**

Jute is not only a major textile fiber but is also a raw material for non traditional and value added non-textile products. Jute is used extensively in the manufacturing of different types of traditional packaging fabrics, hessian, sacking, carpet backing, mats, bags, tarpaulins, ropes and twines.

Recently jute fibers are used in a wide range of diversified products: decorative fabrics, chic-saris, ethnic dresses, soft luggage carrier, footwear, greeting cards, molded door panels and other innumerable useful consumer products which is supported by several technological developments. Today jute can be used to replace expensive fibers and scarce forest materials and can be economical to people. The production of diversified jute products, consumer products, fashion products is carving out new Export marketing. The Indian Jute Industries Research Association (IJIRA) in association with Indian Jute Industry has recently developed a Hydrocarbon free jute bags- a food grade jute bags and clothes confirming to international standard specifications. These bags are used for packaging food stuffs and are in great demand throughout the world. Jute fibers, the main product is extracted from the bast of plants by retting which is a method of separation and loosening of the fibers from the sticks by the decomposition of the cementing materials through Microbial action. Apart from the fibers, plant consists of useful parts that can be utilized in various economical ways just like Jute sticks, Jute Caddies, Jute Leaves, Jute Root Cuttings.

**a) Jute sticks :** It is a woody core of jute plants left after the fiber is taken away on completion of retting as a major agro-residue[6]. It approximately constitutes 40 percent of the green plant while the leaves are mostly used as manure, about 80 percent of the sticks are used as fuel wood by villagers and 15 percent as structural materials for fencing. But it is a potential raw material for the production of particle boards, paper and paper boards. Jute sticks are classified as hardwoods, and the nation produces about 3.0 million tonnes of them annually.[2,5]. Several other products can be made from Jute stick, for example: Oxalic acid, Charcoal, Viscose Rayon, Carboxymethyl Cellulose, Furfural [5]

**b) Jute Caddies:** The caddies are the major industrial waste from the jute sector. The proximate analysis of the jute caddies shows the volatile matter approx 40 percent, fixed carbon 12-13 percent with a gross calorific value as 3200-3300 kcal/kg [5]. Jute caddies constitutes about 4-6 percent of total jute consumed in the mills. These are mainly thrown away as waste material or charged into the conventional boilers of the mills. One kilogramme of jute caddies is equal to 0.635 kg of coal or 0.33 kg of mineral oil when taking into account the calorific values of 5200 kcal/kg of coal and 10,000 kcal/kg of mineral oil.[7]. Jute mills are energy intensive where either electrical or steam energy is consumed for running the machinery continuously. It is estimated that the energy cost is 8 percent of the total cost of production. The efficiency of jute caddies as a fuel can be increased by compaction and briquetting ie, by:

(a) Thermochemical conversion such as Pyrolysis which is heating at high temperature with limited

supply of oxygen, and  
(b) Generation of bio-gas and utilization of the spent slurry in bio-gas production for manuring or for growing mushroom.

Both these processes are environmental friendly. By enriching the rhizosphere soil, the slurry can be used as manure to increase the production of jute crop by approximately 50% [8]. Fibrous fleeces can be mechanically bonded together via needle punching without the use of a binder or other chemical [9]. In order to improve the compatibility of jute fiber and resin chemical or biochemical, modification of the substrates is mandatory. In addition to their reduced cost, jute-reinforced composites are expected to reduce machinery wear and tear because they use natural fibres rather than glass fibres. Jute's greater specific modulus and lower specific gravity have been considered as a beneficial benchmark for switching from glass fibres to jute. A variety of composite products were developed with jute non-wovens pre-treated with alkali followed by scouring and bleaching. The advancement of non-woven technology makes it possible to produce fabrics without using the standard spinning and weaving processes. [2,4].

**Products Made Of Composites From Jute Caddies:** In order to make Fibre Reinforced Plastics (FRP), Jute Caddies based on non-woven fabrics were discovered to be an appropriate reinforcing material [10]. In certain product applications, jute's lower specific gravity and higher specific modulus are crucial. Corrugated sheet, cooling towers, fan blades, pipes, washbasins, serving trays, speaker boxes, auto parts, tool boxes, traffic signal light cases, chairs, table tops, country boats, etc. are among the products created with these applications. [2,4].

**Future Prospects for the Development of Diversified Jute Caddies Products:** Jute caddies may be pre-treated for product diversification and value addition. Textile pre-treatment methods like scouring, bleaching, and grafting are used to improve the quality of jute material. [11,12,13] noted that grafting polymers based on monomers like methacrylonitrile and ethyl methacrylate onto jute fibre could improve its dimensional stability and hydrophobicity with a slight reduction in breaking load. Jute-based fiberboard and fiber-reinforced plastics may be developed by applying such polymer finishing to cleaned jute caddies. The development of nonwoven household upholstery may result from the conversion of jute caddies into needlepunched nonwoven fabrics that are 100% jute based or jute/cotton based, then functionally finished to add dimensional stability, flame retardancy, and water resistance. [14,15]. The suitability of bastfibers for pulp and papermaking is determined by factors such as the flexibility, slenderness, and Runkel ratios [16]. Jute caddies have fibres that range in length from 2.0 to 3.0 mm, making them an excellent source for pulp and papermaking. Blending high-quality jute fibre with pectinolytic-treated jute waste can improve the mechanical properties of the resulting composite product [17]. High moisture-holding capacity wooden chips are used as cooling pads in subtropical climates [18,19, 20]. Because jute is hygroscopic, it can be used in place of traditional wooden chips in cooling pads [18, 19, 20]. Traditionally, a partially automated spinning system is used to spin bastfibers into yarns [21]. Since it is a bast fibre, it can be combined with other vegetable fibres to make crafts or decorative items.

**Jute Caddie Biogas Production:** By using cattle dung as an inoculum source for anaerobic fermentation in digesters, Jute Caddies can be used to produce biogas with a methane (CH<sub>4</sub>) content of at least 55% by volume. Applying a mild caustic soda solution to the Caddies beforehand can shorten the time it takes for the gas to be produced. Because jute candies break down slowly, they can produce larger amounts of biogas. [22,23].

**Making Briquettes Out of Jute Caddies:** When combined with other agricultural residues such as rice husk, sawdust, and jute stick, jute caddies can be briquetted at the ideal moisture content of 10% to 15%. Jute caddies briquettes were found to have a gross calorific value of 3000–3200 Kcal/kg [24]. One kilogramme of jute caddies briquettes is equal to 0.635 kg of coal or 0.33 kg of mineral oil when compared to coal (5200 kcal/kg) and mineral oil (10,000 kcal/kg). [2,5,18].

**Reduced Production of Jute Caddies:** The morphology of the retted fibre, the type of retting process, and the quality of the jute fibre can all affect the formation of caddies [18]. They stated that retting from C-718 and OF-390 varieties produced higher quality and quantity of white fibres with fewer cuttings than other varieties like C.olitorius (OM-1) and from C.capsularis (C-2035, C-2005, and C-2143) in all respects. According to [25, 26], choosing high-quality jute fibres may also help to reduce the production of jute candies. It was also suggested that 276 Tex, a type of jute yarn, performs better at medium speeds than at any other breaker card cylinder speed, which also helps to reduce the production of jute candies.

**Customised Paper Made with Jute Caddies:** Pretreatment, mechanical pulping, beating, sheet creation, drying, trimming, and calendaring are just a few of the unit operations that can be used to turn jute Caddies from the mills into hand-made paper [27]. Owing to its lengthy fibre, Jute Caddies are crucial to the Paper Industries. [28,29].

**c) Jute Leaves :** These are the by-products from jute plant. However, it contains all the vital nutrients mandatory for human body as it is a rich source of protein, fat, carbohydrate, calcium, phosphorus and vitamins like A, B and C [30]. It is also observed that jute leaves are good to fight dysentery, stomach pain, ulcer and other issues related to digestive system. It also helps in developing the immune system of children suffering from cough. The oils extracted from jute leaves are effective to heal skin diseases. Even though experiments revealed that these jute leaves can help people look younger due to its high antioxidant activity and reduces the appearance of wrinkles and fine lines on their face and body. Therefore, it is an evidence that jute leaves are quite nutritious and contain many health benefits. Its application in functional foods and hygienic preparations can play a major role in food processing industries as well and particularly in the medicine sector [2,5,18].

**\*d) Jute Root Cuttings:** It is another industrial waste in the jute sector, which are hard and un-spinnable portion of jute reed detached before processing. A specific fungus *Penicillium corylophilum*, has been isolated which has been found to soften the hard barks without any adverse effect on fibre cellulose. Application of the fungus with mineral oil emulsion at the time of piling facilitates processibility of the inferior material to make finer product [10].

**Conclusion:** The future of jute crop will depend upon the value added diversified products from jute byproducts. With the application of cutting edge technologies emerged from research and development, new products with various end uses will bring sea changes in jute sector. Every portion of agricultural and industrial wastes of jute crop can be processed into useful products by application of physical, chemical, mechanical or biological techniques. Hence in near future, it will help in the socio-economic development of the farmers in villages in particular and national economy in general. Lifestyle of consumers are now dictated by fashion trend to a considerable extent. Besides, this concept of fashion keeps on changing constantly. Customers are becoming more and more demanding in terms of quality, design etc. They also want newer fabric varieties to choose from. Therefore, a rethinking along with reintegration is needed in the textile production processes and the type of textiles to be produced in order to satisfy the customer's requirement. In this context, it is worthwhile to channelize a part of the production facilities for the manufacturer of such unconventional and novel textiles from natural fibers. This will help to create niche market segments enabling textile manufacturers to survive in this fast changing competitive sector.

#### References:

- [1] Mahapatra, B.S. M.Sabyasacchi, M.K. Sinha and A.K. Ghorai, 2009. Research and Development in Jute (*Corchorus* sp.) and allied fibres in India: A review. *Indian J. Agron.*, 54: 361-373.
- [2] Nayak,L. and Roy, A. (2011)Utilization of jute by products- A review., *Agricultural Review*,32(1): 63-69.
- [3] P.K. Ganguly, S.K. Bhaduri and A. Day Jute caddies- A potential raw material for hand-made paper *Journal of scientific & industrial research* Vol.63, May 2004, pp. 417-419
- [4] L.K. Nayak, L. Ammayappan and D.P. Ray.,Conversion of jute caddies (jute mill waste) into value added products: A review, *Asian Journal of textile*, 2012, 2(1), 1-5.
- [5] Bhattacharyya and Paul et.al, Jute crop residues and waste, *Environmental and Agriculture*, 2006.
- [6] Pandey S.N., Ghosh I.N., Dey A., Utilization of nonwood raw materials for Pulp, Paper and Board, *Research and Industry*, 1995, 40, 285-288.
- [7] Samani A, Pandey K K & Reddy K S, Economics of biomass energy conversion system, *Wood News*, 13 (2003) 22
- [8] Banik, S. and R. Nandi, 2000. Effect of supplementation of rice straw with biogas residual slurry manure on the yield, protein and mineral contents of *Volvariella volvacea* mushroom. *J. Sci. Ind. Res.*, 59: 407-412.
- [9] Mazumder, A.K., S.K. Bhattacharyya and S.C. Saha, 2001. "Case studies on field trials with jute-based agricultural non-woven geo-textiles" *Proceedings of the International Seminar on Technical Textiles*, June 2-3, 2001, SARMIRA, Mumbai, India, pp: 125-127.
- [10] Rana, A.K., A. Mondal and K. Jayachandran, 1999. Jute composites: Properties and applications in packaging. *Packag. India*, 3: 15-19.
- [11] Shahidullah, M., M. Rabiul Islam, M.M.A. Sayeed, M. Kamal Uddin and A.B.M. Abdullah, 2007. Improvement of light fastness properties of dyed jute fabrics through pretreatment. *J. Applied Sci.*, 7: 3791-3795

- [12] Venkidusamy, P., L. Ammayappan and G. Pandiyaraj, 2002. Dyeing of jute with disperse dye using PVA as dispersing agent. *Man Made Text. India*, 45: 287-289.
- [13] Mondal, M.I.H., F.I. Farouqui, M.A. Hanif, G.M.S. Rahman and M.A. Hoque, 2005. Grafting of methacrylonitrile and ethyl methacrylate onto jute fibre: Physico-chemical characteristics of grafted jute. *J. Applied Sci.*, 5: 1767-1771.
- [14] Azad, A.K.M., M.M. Alamgir Sayeed, S.M. Golam Kabir, A.H. Khan and S.M. Badier Rahman, 2007. Studies on the physical properties of jute-cotton blended curtain and 100% cotton curtain. *J. Applied Sci.*, 7: 1643-1646.
- [15] Kamal Uddin, M., M.A. Hussain, K.A. Rahman and M.M.A. Sayeed, 2002. Improvement of light fastness of basic dyes on jute. *J. Biological Sci.*, 2: 378-379.
- [16] Olotuah, O.F., 2006. Suitability of some local bast fibre plants in pulp and paper making. *J. Boil. Sci.*, 6: 635-637.
- [17] Ahmed, Z., F. Akhter, M.A. Hussain, M.S. Haque, M.M.A. Sayeed and M.A. Quashem, 2002. Researches on jute and allied fibre plants. *Pak. J. Biol. Sci.*, 5: 812-818.
- [18] Nayak, L.K. and A.K. Majumder, 2011. Evaluation of jute-fibre based wetted pads in evaporative cooling operations. *J. Indian Chem. Soc.*, 88: 1619-1623
- [19] Nayak K., Deb Prasad Ray, Vidya Bhushan Shambhu, Appropriate Technologies for Conversion of Jute Biomass into Energy , *International Journal of Emerging Technology and Advanced Engineering*, 3(3), 2013, 570-576
- [20] Nayak, L.K., A.K. Roy and S. Das, 2011. Some characteristics of jute caddies with reference to briquetting and gasification. *J. Indian Chem. Soc.*, 88: 599-601.
- [21] Das, P.K., D. Nag, S. Debnath and L.K. Nayak, 2010. Machinery for extraction and traditional spinning of plant fibres. *Indian J. Trad. Knowledge*, 9: 386-393
- [22] Banik, S., S.K. Bhattacharyya, S.N. Pandey, D. Paul and D. Sardar, 1993. Biogas production from jute caddies: A lignocellulosic waste. *Res. Ind.*, 38: 165-167
- [23] Gunjan De and GaurabBhowmick, Using Biomass as fuel substitute to reduce fuel cost in locomotive, *International journal on theoretical and applied research in mechanical engineering (IJTARME)*, Volume-2, Issue-3, 2013
- [24] Anonymous, 2006. Annual report 2005-06. National Institute of Research on Jute and Allied Fibre Technology, 12 Regent Park, Kolkata, India
- [25] Rafiqul Islam, M., S. Akhter, M. Nuruzzaman and A.K.M. Shahadat Hossain, 2002. Study of physical and mechanical parameters of some tossa jute (*Corchorus olitorius*) varieties released by India and Bangladesh. *J. Biological Sci.*, 2: 307-308.
- [26] Mahabubuzzaman, A.K.M., L.B. Lutfar, M.K. Kabir and N. Chowdhury, 2002. Study of the effect of speed variation at breaker card cylinder on fibre length and yarn quality. *Asian J. Plant Sci.*, 1: 648-649.
- [27] Ganguly, P.K., S.K. Bhaduri and A. Day, 2004. Jute caddies: A potential raw material for handmade paper. *J. Sci. Ind. Res.*, 63: 417-419
- [28] Divya Prakash, Satish Kumar, N.P.Lamba " Degradation of carcinogenic compounds by using Chlorine dioxide in Jute Cady pulp effluents" *International Journal of Chemical Sciences*, *Int. J. Chem. Sci.*: 14(2), 2016, 608-616
- [29] Divya Prakash, Shalini Singh, Satish Kumar, " Influence of Chemical Dose Splitting on Reduction of Carcinogenic Compounds during Paper Mills" *Oriental Journal of Chemistry*, Vol 33, 2017
- [30] Shitanada D., Wanjala N.V., "Effect o Effect of Different Drying Methods on the Quality of Jute (*Corchorus olitorius* L.)" *Drying Technology* 24(1):95-98 · February 2006